

Aggregates – Quality Requirements

| | limestone |
|--------------------------------|-----------|
| Minimum requirements | |
| chemical (%): | |
| CaO | > 50 |
| SiO ₂ | < 1 |
| Al ₂ O ₃ | < 1 |
| Na ₂ O | < 0,03 |
| K ₂ O | < 0,13 |
| ZnO | < 0,05 |
| H ₂ O | < 9 |
| mechanical: | |
| grain size (mm) | < 3 |